



Test Report No. 68.441.17.0948.01A
Dated 2017-03-31

Applicant : AAB Co., Ltd.
Address : No.1028 Jinxi Block, Kangwang North Road, Liwan District,
Guangzhou, Guangdong, China
Sample Receive Date : 2017-03-21
Test Period : From 2017-03-21 to 2017-03-30
Sample Description : STAINLESS STEEL PENDANT
Style No. : PSS872/ ANTIQUE COPPER*
Supplier : AAB Co., Ltd.
Buyer : Not Provided
Country of Origin : China
Exported to : Not Provided
Applicant's Reference : Not Provided

Note:

- 1. The submitted samples were Not Drawn by the Laboratory.*
 - 2. The test item and sample were specified by the client.*
 - 3. The results relate only to the items tested.*
 - 4. The conclusion was drawn according to the client's specification.*
 - 5. The test report shall not be reproduced except in full without the written approval of the laboratory.*
-

Test Report No. 68.441.17.0948.01A
Dated 2017-03-31



Conclusion According To Client's Specification:

SN	Test Item	Conclusion	Failed Component	Failed Result
1	Nickel Release	Pass	-	-

TÜV SÜD Certification and Testing (China) Co., Ltd.
Shenzhen Branch

Prepared by

Wilson

Wilson Wen
CS representative



Reviewed by


Bailey
Bailey Liu
Supervisor



Test Report No. 68.441.17.0948.01A
Dated 2017-03-31



1. TESTED SUBJECT DESCRIPTION

PHOTO	
 <p align="center">A</p>	
001	Copper color metal pendant –A

2. TEST RESULT

2.1. NICKEL RELEASE

Entry 27 of Regulation (EC) No. 552/2009 amending Annex XVII of REACH Regulation (EC) No. 1907 / 2006 (Formerly restricted under Directive 94/27/EEC)

Test method: With reference to EN12472:2005+A1:2009 and (or) EN 1811:2011+A1: 2015.

[Reporting limit: 0.05 µg/cm²/week]

SAMPLE NO	NICKLE RELEASE (µg/cm²/week)		SIZE OF TEST SAMPLE AREA (cm²)	VOLUME OF TEST SOLUTION USED (mL)	LIMIT (µg/cm²/week)
001	Specimen 1	0.232	16.4	20.0	<0.5
	Specimen 2	0.123	16.4	20.0	
	Specimen 3	0.247	16.4	20.0	

Note:

- “<” denotes less than
- “µg/cm²/week” denotes microgram per square centimeters per week
- “cm²” denotes square centimeters
- “mL” denotes milliliter
- A larger volume to surface area ratio was used due to the purpose of fully immersion.
- According to EN 1811:2011 + A1:2015 clause 9.2.2.2, the article shall be accepted and be permitted to be placed on the market if the measured value is <0.88 µg/cm²/week.

-- END OF THE TEST REPORT --